HIGH TEMPERATURE PAINT SPECIFICATION

APPLICATION DATA 10.02-6
Page 1
January, 2011
Supersedes September, 2009

DeZURIK

Name:	Thurmalox 280C Aluminum
Material:	Silicone Aluminum
Color:	Aluminum
Application:	Spray, Brush, Roll
% Solids by Volume:	25% ± 2.0%
Theoretical coverage:	400 mil sq. ft. per gallon
Application Temperature at 50 % RH	50 °F – 120 °F(10°C-50°C)

Air Drying Time @ 70° F (21.1° C) & 50 % RH:

To touch:	30 minutes
To re-coat:	8 hours
To ship:	24 hours

VOC:	3.5 lbs/gal.
Minimum Surface Prep:	SSPC-SP-10
Flash Point:	45° F (7.2° C)
Performance Criteria:	Temperature Resistance (Dry): Continuous 1,200° F (649° C)
DeZURIK Standard Thickness:	1.5 –2.0 mils dry 6.0 –8.0 mils wet