



Name: Carbit 21A4 Black Bituminous Coating
Material: Asphaltum Varnish Fed Spec (TT-C-494C)
Viscosity: 110-190 Sec. #4 Ford
Reduction: 3:1
Application: Spray
Weight: 7.3 Pounds per Gallon
% Solids by Volume: 46% min.
Gloss: 90° min. (60° HEAD)
Surface Preparation: SSPC-SP-10
Theoretical Coverages: 737 @ 1.0 mils
Air Drying Time @ 77° F (25° C):
 Dust Free: 5 minutes
 Tack Free: 1 hour
Flash Point: 50° F (10° C) SETA
Standard Thickness: 1-2 mils